

Image not found

IMECO [http://www.imeco.co.cu/sites/default/files/logo\\_0.jpg](http://www.imeco.co.cu/sites/default/files/logo_0.jpg)

Published on *IMECO* (<http://www.imeco.co.cu>)

[Home](#) > Rojo Campiña Marble

---

## Rojo Campiña Marble

Image not found

[http://www.imeco.co.cu/sites/default/files/styles/imagen\\_interior/public/marmol\\_rojo\\_compania\\_marble.png?itok=hc9uoSQ8](http://www.imeco.co.cu/sites/default/files/styles/imagen_interior/public/marmol_rojo_compania_marble.png?itok=hc9uoSQ8)

Variety: ROJO CAMPIÑA MARBLE Deposit: Real Campiña Localization: Aguada de pasajeros.  
Cienfuegos Rock: Limestone organogenic fossiliferous Color: Red with yellowish spots sometimes  
Character and Use Ornamental: The average grain mass, crystallized with abundant stylolites oriented in variable directions. This variety does well to grinding after coating. It is recommended for floors and veneer, mainly indoors, also of great use in rustic, especially outdoors. Polishing and shining good. Mechanical  
Physical parameters: ? Volumetric Mass: 2.47 - 2.7 g/cm<sup>3</sup>. ? Absorption: 1.9 - 2.9%. ? Compressive strength: Dry - 350 to 900 kgf/cm<sup>2</sup>. ? Flexural strength: 60 Kgf/cm<sup>2</sup> ? Abrasives - 0.18 - 1.09 g/cm<sup>2</sup> ? Porosity - 3.0% Chemical parameters: ? SiO<sub>2</sub>: 1.24 % ? MgCO<sub>3</sub>: 11.23 % ? Al<sub>2</sub>O<sub>3</sub>: 1.3 % ? SO<sub>3</sub>: 0.08 % ? Fe<sub>2</sub>O<sub>3</sub>: 0.08 % ? NaO < 0.1 % ? CaCO<sub>3</sub>: 83.87 % ? CaO: 47.12% ? CO<sub>2</sub>: 47.12 % ? K<sub>2</sub>O < 0.1 %

[Contact by email](#)

---

**Source URL:** <http://www.imeco.co.cu/en/rojo-campina-marble>